



## PRODUCT DATA SHEET

<b>Product Brand:</b>	<b>iCARB-MF7-C12-A3</b>
<b>Product Type:</b>	<b>Magnesia Carbon Brick</b>
<b>Product Description:</b>	Carbon bonded brick based on a blend of large crystal fused magnesia, high purity large crystal fused magnesia, high purity natural flake graphite, with anti-oxidant additions

### Control Properties:

<b>As Received:</b>				
Test Property	Test Method	Units	Typical	
Bulk Density:	DIN EN 993-1	g/cm <sup>3</sup>	2.98	
Apparent Porosity:	DIN EN 993-1	%	3.3	
Cold Crushing Strength:	DIN EN993-5	N/mm <sup>2</sup>	45	
<b>Coked:</b> ( 2hrs at 1000 °C )				
Bulk Density:	DIN EN 993-1	g/cm <sup>3</sup>	2.93	
Apparent Porosity:	DIN EN 993-1	%	9.3	
Cold Crushing Strength:	DIN EN993-5	N/mm <sup>2</sup>	30	
P.L.C	PRE/R 19	%	-0.1	
<b>Chemical Analysis:</b> ( The presence of antioxidants will affect any analysis on an ignited basis )*				
Residual Carbon	ASTM C831-98	%	12.00*	
MgO	DIN EN 955-5	%	80.84	
SiO <sub>2</sub>	DIN EN 955-5	%	0.60	
CaO	DIN EN 955-5	%	1.10	
Fe <sub>2</sub> O <sub>3</sub>	DIN EN 955-5	%	0.54	
Al <sub>2</sub> O <sub>3</sub>	DIN EN 955-5	%	4.92	

Industrial Technologies & Energy

<b>Version: 01</b>	The values given are indicative of expected property values for product tested. Please note this data is supplied for information only and as such does not constitute a product specification	<b>Print Date : 2021-09-26</b>
--------------------	--	--------------------------------